

## UV Tracer

A dispersion of a perfluoroether lubricant dispersed in a perfluoroalkane solvent intended for electrical contact protection. Excellent high temperature performance and material compatibility.

Typical Properties of the Oil		Typical Value	Test Method	
<b>Recommended Service Range (°C)</b>		-50 to 225		
<b>Base Oil</b>	Type	Perfluoropolyether		
	Kinematic Viscosity	100°C	45 cSt	ASTM D-445
		40°C	150 cSt	ASTM D-445
	Viscosity Index		340	ASTM D-2270
	Flash Point	°C	300.0000	ASTM D-92
	Pour Point	°C	< -70	ASTM D-97
	Density	25°C	1.88 g/cm <sup>3</sup>	ASTM D-1480
	Evaporation	24 hour(s) 150°C	< 0.1 %	ASTM D-972
Typical Properties of the Grease		Typical Value	Test Method	
<b>Color, Appearance</b>		White.		
<b>Thickener</b>		Silica		
<b>Density</b>	25°C	1.8 g/cm <sup>3</sup>	NYE CTM	
<b>Evaporation</b>	24 hour(s) 100°C	0.1 %	ASTM D-972	
Typical Properties of the Solvent		Typical Value	Test Method	
<b>Chemical Composition</b>		Hydrofluoroether		
<b>Concentration by Weight</b>		75 %		
<b>Density</b>	25°C	1.7 g/cm <sup>3</sup>	ASTM D-1480	

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product MSDS for detailed safety information because this product. (1405)