

## UV Tracer

A light viscosity, lithium soap thickened, polyolester grease  
Intended for electrical contact and small precision bearing applications.

Ford: WSS-M1C255-A1

Lubricant Properties		Typical Value	Test Method
<b>Recommended Service Range (°C)</b>		-54 to 150	
<b>Thickener</b>		Lithium Soap	
<b>Base Oil</b>	Type	Ester	
	Kinematic Viscosity	100°C	4.1 cSt
		40°C	18.5 cSt
	Viscosity Index		125
	Flash Point	°C	256
	Pour Point	°C	-67
<b>Typical Properties of the Grease</b>		<b>Typical Value</b>	<b>Test Method</b>
<b>Color, Appearance</b>		Tan, Smooth	
<b>Penetration (1/10 mm)</b>	NLGI Grade	2	ASTM D-217
	Unworked	267	ASTM D-217
	Worked	60X	281
<b>Density</b>		25°C	0.91 g/cm <sup>3</sup>
<b>Oil Separation</b>	24 hour(s)	100°C	4.6
			FTM 791, Method 321.2
<b>Evaporation</b>	24 hour(s)	100°C	0.3 %
			NYE CTM

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1503)