

A PTFE thickened, medium viscosity, completely fluorinated grease for use in high temperature applications exposed to fuels or aggressive chemicals. It possesses excellent thermo-oxidative stability and low vapor pressure characteristics.

Ford: WSB-M1C242-A, GM: 9986173

Lubricant Properties		Typical Value	Test Method
<b>Recommended Service Range (°C)</b>		-50 to 225	
<b>Thickener</b>		PTFE	
<b>Base Oil</b>	Type	Perfluoropolyether	
<b>(Uniflor 8510)</b>	Kinematic Viscosity	100°C	15.8 cSt
		40°C	65 cSt
	Viscosity Index		258
	Pour Point	°C	-54
		ASTM D-445	ASTM D-97
Typical Properties of the Grease		Typical Value	Test Method
<b>Color, Appearance</b>		White, Smooth	
<b>Penetration (1/10mm)</b>	Worked	60X	281
			ASTM D-217
<b>Density</b>		25°C	1.95 g/cm <sup>3</sup>
			NYE CTM
<b>Oil Separation</b>	24 hour(s)	150°C	6.8
			ASTM D-6184
<b>Evaporation</b>	24 hour(s)	150°C	1 %
			NYE CTM

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1504)