

A melamine cyanurate thickened, medium viscosity, perfluoropolyether grease intended for high temperature electrical connectors. Provides excellent insertion force reduction and long-term contact protection.

GM: 2793M

Lubricant Properties			Typical Value	Test Method	
Recommended Service Range (°C)			-70 to 225		
Thickener			Melamine Cyanurate		
Base Oil			Perfluoropolyether		
(Uniflor 8910)	Kinematic Viscosity	100°C	27 cSt	ASTM D-445	
		40°C	88 cSt		
		-40°C	2632 cSt		
	Viscosity Index		336	ASTM D-2270	
	Flash Point		°C	>398	ASTM D-92
	Pour Point		°C	-73	ASTM D-97
Typical Properties of the Grease			Typical Value	Test Method	
Color, Appearance			White, Smooth		
Penetration (1/10 mm)	NLGI Grade		2	ASTM D-217	
	Unworked		271		
	Worked		60X 279		
Density	25°C		1.78 g/cm ³	ASTM D-1480	
Oil Separation	24 hour(s)	100°C	4.8	ASTM D-6184	
Evaporation	24 hour(s)	100°C	0.05 %	NYE CTM	

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1506)