



A lithium soap thickened, medium viscosity silicone grease fortified with PTFE for added lubricity. Ideal for plastic on plastic and plastic on metal applications and control cables.

GM: 9986172

Lubricant Properties		Typical Value	Test Method
rice Range (°C)		-40 to 200	
		Lithium Soap	
Туре		Dimethyl Silicone	
Kinematic Viscosity	100°C	171 cSt	ASTM D-445
	40°C	410 cSt	ASTM D-445
Viscosity Index		454	ASTM D-2270
Flash Point	°C	350	ASTM D-92
Pour Point	°C	-45	ASTM D-97
Typical Properties of the		Typical Value	Test Method
Grease			
		White, Smooth	
NLGI Grade		1	ASTM D-217
Unworked		313	ASTM D-217
Worked	60X	331	ASTM D-217
24 hour(s)	100°C	1.5	ASTM D-6184
Evaporation 24 hour(s)	100°C	0.05 %	ASTM D-972
	100°C	0.5	
	Type Kinematic Viscosity Viscosity Index Flash Point Pour Point Typical Properties of Grease NLGI Grade Unworked Worked 24 hour(s)	Type Kinematic Viscosity Viscosity Index Flash Point Pour Point C Typical Properties of the Grease NLGI Grade Unworked Worked Worked 24 hour(s) 100°C Type 100°C 100°C	rice Range (°C) -40 to 200 Lithium Soap Lithium Soap Type Dimethyl Silicone Kinematic Viscosity 100°C 171 cSt 40°C 410 cSt Viscosity Index 454 Flash Point °C 350 Pour Point °C -45 Typical Value Grease White, Smooth NLGI Grade 1 Unworked 313 Worked 60X 331 24 hour(s) 100°C 1.5 24 hour(s) 100°C 0.05 %

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1504)