



A silica thickened, medium viscosity, synthetic hydrocarbon grease intended for mechanical components requiring a light amount of damping.

DaimlerChrysler: MS-10232

	Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)		-30 to 120		
Thickener			Silica	
Base Oil	Туре		Polyalphaolefin	
	Kinematic Viscosity	100°C	479 cSt	ASTM D-445
	_	40°C	5070 cSt	
	Viscosity Index		274	ASTM D-2270
	Flash Point	°C	274	ASTM D-92
	Pour Point	°C	-30	ASTM D-97
	Typical Properties of	the	Typical Value	Test Method
	Grease			
Color, Appearance			Tan to Light Brown, Smoot	:h
Penetration	Unworked		264	ASTM D-217
(1/10 mm)	Worked	60X	283	
		10K	303	
		100K	363	
	NLGI Grade		2	
Density		25°C	0.86 g/cm ³	NYE CTM
Oil Separation	24 hour(s)	100°C	1.2	ASTM D-6184
Evaporation	24 hour(s)	100°C	0.1	NYE CTM

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1504)