

Rust Inhibited

A lithium soap thickened, light viscosity synthetic hydrocarbon grease intended for electrical switch contacts. Enhanced temperature stability for light mechanical applications.

Ford: WSD-M1C234-A2

| Lubricant Properties | | Typical Value | Test Method |
|---------------------------------------|---------------------|-------------------|------------------------|
| Recommended Service Range (°C) | | -54 to 125 | |
| Thickener | | Lithium Soap | |
| Base Oil | Type | Polyalphaolefin | |
| | Kinematic Viscosity | 40°C | 33 cSt |
| | | 100°C | 6 cSt |
| | Viscosity Index | | 141 |
| | Flash Point | °C | 250 |
| | Pour Point | °C | -65 |
| Typical Properties of the Grease | | Typical Value | Test Method |
| Color, Appearance | | Light Tan, Smooth | |
| Penetration (1/10 mm) | Worked | 60X | 273 |
| | Unworked | | 266 |
| | NLGI Grade | | 2 |
| Density | | 25°C | 0.83 g/cm ³ |
| Oil Separation | 24 hour(s) | 100°C | 2.9 |
| Evaporation | 24 hour(s) | 100°C | 0.07 % |

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1506)